



## TECHNICAL DATA SHEET

# S309

### PREMIUM POLYMER MODIFIED TILE ADHESIVE

#### DESCRIPTION:

S309 is a premium grade polymer modified highly flexible, white cement based tile adhesive

#### PRODUCT FEATURES:

- C2TES2 Classification
- Highly Flexible
- Excellent non slump properties
- Immersible
- Suitable for use over early age concrete, screed/render

#### AREAS OF USE

- Floor and wall tiling to internal and external areas for commercial and residential
- Internal and external wet areas
- Bonding of porcelain and vitrified tiles, mosaic, terracotta and natural stone (not moisture sensitive)
- Immersed areas - pools, spas and water features
- Large format tile installations

#### SUBSTRATES:

- Concrete
- Sand/cement screed
- Sand/cement render
- Compressed fibre cement sheeting
- Ceramic tile underlay
- Plasterboard
- Approved waterproof membranes\*

\* Contact PCP Products for recommendations

#### SUBSTRATE PREPARATION:

- All surfaces must be clean, sound, dry, and free from dirt, dust, existing coatings, sharp and foreign objects and all other loose and contaminating materials
- All surfaces and substrates must be fit for purpose and installed as per manufacturers recommendations, relevant building codes and standards
- Concrete slabs must be allowed to cure for at least 28 days and have a wood float finish
- Steel trowelled and dense concrete surfaces must be mechanically abraded to roughen surfaces, or primed with a suitable non-porous primer
- Rendered and screeded surfaces must be allowed to cure for at least 7 days
- Existing tiled surfaces must be sound and well bonded to the substrate. Surface of tiles to be mechanically roughened to remove at least 80% of the tile glaze for direct fixing. Alternatively prime tiles with a suitable non-porous primer

#### PRIMING:

Highly porous and non-porous surfaces should be primed before the installation of S309 using suitable primers

#### MIXING:

- Add 4.5 litres of clean water into a clean mixing pail
- Gradually add S309 adhesive and mix continuously using an electric stirrer with mixing paddle attachment to form a smooth, lump-free consistency
- Always add powder to the liquid
- Allow the adhesive to stand for 3 minutes and re-mix before using

## TECHNICAL DATA SHEET

### APPLICATION:

- Preparation and tiling to be carried out as per AS 3958
- Apply the adhesive onto the substrate using a suitable notch trowel appropriate to the size of the tile
- Apply adhesive to the substrate at a rate of 1m<sup>2</sup> at a time to avoid the adhesive skinning before tiles can be laid
- Skinned adhesive must be removed and replaced with fresh adhesive
- Place tiles and press them into the wet bed of adhesive using a sliding action, preventing voids and achieving full coverage of adhesive under the tiles
- The final bed thickness of the adhesive should be 2mm for wall tiling and 3mm for floor tiling
- Avoid disturbing the tiled surface for at least 24 hours after completion of tiling

### COVERAGE:

- Approximately 6-7m<sup>2</sup> per 15kg bag (10mm Notched trowel)

### GROUTING:

- Grouting application can commence after adhesive has cured for 24 hours\*
- Remove any dried adhesive that has leached into the grout joint before grouting

\*Drying times may be extended in humid conditions and colder temperatures

### CLEAN UP:

- Remove wet adhesive from face of tiles using a damp sponge
- Tools and equipment can be cleaned with water while the adhesive is still wet
- Dried adhesive can only be removed by mechanical means

### HEALTH & SAFETY:

Refer to the most recent Safety Data Sheet (SDS) for information and advice regarding physical, ecological, toxicological and other safety-related data including handling, first aid, storage and disposal

### LIMITATIONS:

- Do not apply when surface or ambient temperatures are above 35°C or below 5°C.
- Not suitable for fixing tiles directly to timber flooring.
- Not suitable for use with moisture sensitive stone
- For detailed advice on applications not mentioned in this TDS, contact PCP.

### SHELF LIFE / STORAGE:

A bag of S309 will have a shelf life of approximately 12 months when stored off floors in a cool, dry environment

### PRODUCT INFORMATION

Colour	White
Shelf life	12 months
Packaging	15kg bags
Coverage	7m <sup>2</sup>

### APPLICATION PROPERTIES

Figures based on @ 23°C, 50% RH\*

\*Temperature, humidity and tile/surface porosity will vary dry times

Mixing Ratio	4.5 litres water/bag
Open Time	30 minutes
Adjustment Time	40 minutes
Pot Life	1 hour
Grouting Time	24 hours
Ready for wet area service	3 days

### PERFORMANCE PROPERTIES (ISO 13007)

Tensile adhesion strength after 28 days	≥ 1MPa
Water immersion	≥ 1MPa
Freeze/thaw	≥ 1MPa
CLASSIFICATION	C2TES2